

AMENDMENTS TO THE SPECIFICATION

On page 3, amend the paragraph [10] of the application as follows:

Preferably, the vacuum wall is made of polyurethane where diol compound having a molecular weight of 4,000 ~ 6,000 is mixed with methylene- diisocyanate in the ratio of 1 : 8 or to 12.